

# RED FINE STANDARD MURIATE OF POTASH

Grade Code: RFSS

#### TYPICAL CHEMICAL ANALYSIS

Component/Equivalent	Symbol	Unit	Typical	Guaranteed
Potassium Chloride	KCl	%	96.8	
Potassium Oxide	K <sub>2</sub> O	%	61.1	60 Minimum
Sodium Chloride	NaCl	%	2.8	
Moisture	$H_2O$	%	0.02	
Calcium	Ca	%	0.04	
Chloride	Cl¯	%	47.7	
Magnesium	Mg	%	0.04	
Potassium	K	%	50.6	
Sodium	Na	%	1.3	
Sulfate	$SO_4$	%	0.1	
Water Insolubles		%	0.5	

### **PARTICLE SIZE DISTRIBUTION** (SGN 30-37)

THE TILL SIZE DISTRIBUTION (SCHOOL ST)						
	Tyler	US	mm	Typical	Typical	
	Mesh	Mesh	Mesh	Cumulative %	Range %	
Retained on	28	30	0.600	16.2	8 - 35	
	35	40	0.425	34.6	13 - 57	
	48	50	0.300	56.8	35 - 77	
	65	70	0.212	77.7	62 - 91	
	100	100	0.150	91.8	82 - 100	
Passing through	100	100	0.150	8.2	0 - 18	

# PHYSICAL PROPERTIES

Parameter	Unit	Typical/Range	
Bulk density	lb/cu ft	67 - 84	
	kg/m <sup>3</sup>	1073 - 1346	
Angle of repose	degrees	32	

Typical results are based on product expectations at load port.

To the best of Canpotex's knowledge and belief, the information contained herein is accurate and reliable. The analysis values listed as 'Typical' in the above specifications are average values compiled from composite sample analysis and should not be considered a guaranteed specification, unless otherwise noted.

# **Revised July 2024**

<sup>&</sup>lt; signifies "less than" the stated detection limit.